

AMENDMENT TO THE CLAIMS

1. **(Presently Amended)** A process for manufacturing paper and board comprising providing a suspension comprising cellulosic fibres and at least a cellulose reactive sizing agent, dewatering said suspension thereby forming a paper-web, wherein

i) an aromatic-containing cationic vinyl addition polymer is added to the suspension in an amount of from about 0.005 % by weight up to about 1.0 % by weight based on dry pulp, and

ii) an anionic polymer having a weight average molecular weight of up to about 500,000 selected from the group consisting of vinyl addition polymers and condensation polymers is added to the suspension in an amount of from about 0.001 % by weight up to about 3.0 % by weight based on dry pulp,

whereby the aromatic-containing cationic vinyl addition polymer and the anionic polymer are added separately to the suspension.

2. **(Original)** A process according to claim 1, wherein the anionic polymer has a weight average molecular weight in the range from about 10,000 up to about 100,000.


3. **(Original)** A process according to claim 2, wherein the weight average molecular weight is in the range from about 15,000 up to about 75,000.

4. **(Original)** A process according to claim 1, wherein the anionic polymer comprises aromatic monomers having sulphonate groups.

5. **(Original)** A process according to claim 1, wherein the anionic polymer is a vinyl addition polymer having a weight average molecular weight of up to about 500,000.

6. **(Original)** A process according to claim 5, wherein the anionic vinyl addition polymer comprises aromatic monomers.

7. (Original) A process according to claim 6, wherein the aromatic monomers have at least one sulphonate group.
8. (Original) A process according to claim 5, wherein the anionic vinyl addition polymer is polystyrene sulphonate.
9. (Original) A process according to claim 1, wherein the aromatic-containing cationic vinyl addition polymer has a weight average molecular weight of at least about 500,000.
10. (Original) A process according to claim 1, wherein the cationic vinyl addition polymer is prepared from a reaction mixture comprising from about 1 up to 99 mole% of a cationic monomer having an aromatic group.
11. (Original) A process according to claim 11, wherein the cationic monomer having an aromatic group is represented by formula (I)



wherein R_1 is H or CH_3 ; R_2 and R_3 are independently from another a hydrogen or an alkyl group having from 1 to 3 carbon atoms; A_1 is O or NH; B_1 is an alkylene group having from 2 to 8 carbon atoms; Q is a substituent containing an aromatic group; and X^- is an anionic counterion.

12. (New) A process for sizing paper and board comprising adding to a cellulose suspension:

(i) at least one resin derived or cellulose reactive sizing agent or a mixture thereof;

(ii) an aromatic-containing cationic vinyl addition polymer in an amount of from about 0.005 % by weight up to about 1.0 % by weight based on dry pulp; and
(iii) an anionic polymer having a weight average molecular weight of up to about 500,000 selected from the group consisting of vinyl addition polymers and condensation polymers, wherein said anionic polymer is added to the suspension in an amount of from about 0.001 % by weight up to about 3.0 % by weight based on dry pulp; wherein (ii) and (iii) are separately added to the suspension.